

CONCRETE-FINISHA™

Concrete-Finisha™ is an advanced sealer and premium color enhancer for concrete pavers & highly porous materials, replacing traditional coatings.



Typical Applications

Concrete-Finisha™ is suitable for highly porous surfaces, including concrete/clay pavers, saltillo, poured concrete, encaustic tiles, masonry and grout. Use indoors/outdoors on floors, driveways, garages, paths, patios, car parks, pool decks, walls, facades, entertaining areas.

Benefits

- Premium color enrichment and protection against staining and efflorescence
- Replaces traditional acrylic, urethane and epoxy coatings - no cracking and peeling
- Strengthens polymeric sand and makes it water repellent
- UV stable - lasts up to 10 years, then recoat without stripping



VOC Content:

<30 g/L (excluding water) for EPA purposes.

Pack Size

1 Gallon (3.79 mL) and 5 Gallons (18.9 L) container

Precautions

If medical advice is needed, have product container or label at hand. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Avoid release to the environment. Wear protective clothing, eyewear and gloves. Avoid inhaling vapor or spray mist and ensure area is well ventilated.

In case of fire: Use water fog, foam or carbon dioxide to extinguish. The use of dry chemical or dry powder extinguishing agents is not recommended.

If swallowed: Immediately give a glass of water. **If skin contact occurs** remove contaminated clothing and wash skin thoroughly. **If in eyes,** wash out immediately with fresh running water. **If you inhale** vapors or mist, relocate to fresh air. If symptoms persist contact a physician.

Accidents: Spillage - take up mechanically or with absorbent material such as sand or saw dust.

Storage

Keep container tightly sealed in a cool, well ventilated place. It is recommended that this product is best used within seven days from opening to avoid possible spoilage. Product is freeze-thaw stable. Dispose of content / container in accordance with local regulation.

How to Use:

1. **ALWAYS TEST PRODUCT ON A SMALL AREA FIRST and allow a 24-hour cure time to check results.**
2. Ensure surfaces to be treated are dry, clean and free of residues and topical coatings. Apply when surface temperature is between 5 to 35°C (40 to 95°F).
3. Apply Concrete-Finisha™ generously and evenly with a HVLP sprayer (High volume, low pressure sprayer), roller, brush, or similar. Avoid contact with surrounding areas.
4. After a minimum of 30 minutes apply a second coat. Additional coats can be applied at any time to a clean dry surface.
5. Allow a minimum of 30 minutes for second coat of product to penetrate and use a lamb's wool applicator, or similar, to remove any excess product. Regularly wipe applicator clean with a cloth. **Warning: Excess sealer left to dry on surface may make the surface more slippery when wet.**
6. Avoid contact with moisture and traffic for a minimum of 24 hours after application. Full curing takes 7 days.
7. Use methylated spirits, or similar, to clean equipment.
8. When enhancement wears, the clean, dry surface can be recoated with Concrete-Finisha™ without stripping the old sealer.

Notes: (a) Concrete-Finisha™ will not prevent corrosion of acid sensitive surfaces from acidic liquids (including acid rain) or physical wear. (b) Concrete-Finisha™ will darken, and may change the gloss level, of surfaces. Once treated, surface cannot be restored back to the original look. Patchiness (uneven coloring) may become more prominent after applying Concrete-Finisha™. (c) Weather exposure and cleaning methods can affect the treatment over time. (d) Concrete-Finisha™ is only for highly porous surfaces. On more dense surfaces, including natural stone, use Dry-Treat INTENSIFIA™.

Application rates:

Total application rate is approximately 160 to 200 sq ft (16 to 20 sqm) per gallon depending on absorption.